

Epoxy Tank Coating

PRODUCT DESCRIPTION A two pack, FDA compliant epoxy cargo tank coating offering extensive cargo resistance.

INTENDED USES Suitable for the carriage of over 2000 cargoes including clean and dirty petroleum products, vegetable and animal oils, caustic soda and seawater ballast.
For use at Newbuilding or Maintenance & Repair.

PRODUCT INFORMATION	Colour	THA700-Pink, THA701-White, THA702-Grey
	Finish/Sheen	Semi-gloss
	Part B (Curing Agent)	THA703
	Volume Solids	53% ±2% (ISO 3233:1998)
	Mix Ratio	3.50 volume(s) Part A to 1 volume(s) Part B
	Typical Film Thickness	125 microns dry (236 microns wet)
	Theoretical Coverage	4.24 m ² /litre at 125 microns dft, allow appropriate loss factors
	Method of Application	Airless Spray, Roller, Brush
	Flash Point (Typical)	Part A 24°C; Part B 23°C; Mixed 26°C
	Induction Period	30 minutes at temperatures below 25°C

Drying Information	5°C		10°C		25°C		35°C	
Touch Dry [ISO 9117/3:2010]	6 hrs		5 hrs		3 hrs		60 mins	
Hard Dry [ISO 9117-1:2009]	24 hrs		20 hrs		8 hrs		6 hrs	
Pot Life	9 hrs		9 hrs		5 hrs		3 hrs	
Overcoating Data - see limitations				Substrate Temperature				
	5°C		10°C		25°C		35°C	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Interline 704	36 hrs	35 days	24 hrs	32 days	9 hrs	21 days	7 hrs	14 days

REGULATORY DATA	VOC	425 g/lit as supplied (EPA Method 24) 333 g/kg of liquid paint as supplied. EU Solvent Emissions Directive (Council Directive 1999/13/EC) 381 g/lit Chinese National Standard GB23985
------------------------	------------	---

Note: VOC values are typical and are provided for guidance purposes only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

Epoxy Tank Coating

CERTIFICATION

When used as part of an approved scheme, this material has the following certification:

- Food Contact - FDA Compliant: Liquid and Dry Foodstuffs
- Tank Coatings - Recognised Corrosion Control Coating (LR)
- Food Contact - Carriage of Grain (NOHA)

Consult your International Paint representative for details.

SYSTEMS AND COMPATIBILITY

Consult your International Paint representative for the system best suited for the surfaces to be protected. When using in cargo or grey water tanks, consult the Interline 704 Cargo Tank or Grey Water Tanks Application Guidelines.

SURFACE PREPARATIONS

Use in accordance with the standard Worldwide Marine Specifications.

All surfaces to be coated should be clean, dry and free from contamination.

High pressure fresh water wash or fresh water wash, as appropriate, and remove all oil or grease, soluble contaminants and other foreign matter in accordance with SSPC-SP1 solvent cleaning.

NEWBUILDING/MAJOR REFURBISHMENT

Where necessary, remove weld spatter and smooth weld seams and sharp edges.

This product must only be applied to surfaces prepared by abrasive blast cleaning to Sa2½ (ISO 8501-1:2007).

A sharp, angular surface profile of 50-100 microns is recommended.

Any minor areas (consult International Paint) remaining after blast cleaning has been carried out, where the specified standard has not been met, may be prepared by power tooling to Pt3 (JSRA SPSS:1984).

Interline 704 must be applied before oxidation of the steel occurs. If oxidation does occur the entire oxidised area should be reblasted to the standard specified above.

Surface defects revealed by the blast cleaning process, should be ground, welded, or treated in the appropriate manner.

Surfaces may be primed with Interline 982 to 40 microns dry film thickness before oxidation occurs. Alternatively, the blast standard can be maintained by use of dehumidification.

REPAIR

Consult International Paint.

Consult your International Paint representative for specific recommendations.

NOTE

For use in Marine situations in North America, the following surface preparation standards can be used:

SSPC-SP10 in place of Sa2½ (ISO 8501-1:2007)

SSPC-SP11 in place of Pt3 (JSRA SPSS:1984)

Epoxy Tank Coating

APPLICATION	Material is supplied in 2 containers as a unit. Always mix a complete unit in the proportions supplied. (1) Agitate Base (Part A) with a power agitator. (2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.
Thinner	International GTA220. Thinning is not normally required. Consult the local representative for advice during application in extreme conditions. Do not thin more than allowed by local environmental legislation.
Airless Spray	Recommended Tip Range 0.64-0.69 mm (25-27 thou) Total output fluid pressure at spray tip not less than 211 kg/cm ² (3000 p.s.i.)
Conventional Spray	Application by conventional spray is not recommended.
Brush	Application by brush is recommended for small areas only. Multiple coats may be required to achieve specified film thickness.
Roller	Application by roller is recommended for small areas only. Multiple coats may be required to achieve specified film thickness.
Cleaner	International GTA822
Work Stoppages and Cleanup	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA822. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units. Clean all equipment immediately after use with International GTA822. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays. Do not exceed pot life limitations. All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.
Welding	In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. In North America do so in accordance with instruction in ANSI/ASC Z49.1 "Safety in Welding and Cutting."

SAFETY **All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety & Environmental standards and regulations.**

Prior to use, obtain, consult and follow the Material Safety Data Sheet for this product concerning health and safety information. Read and follow all precautionary notices on the Material Safety Data Sheet and container labels. If you do not fully understand these warnings and instructions or if you can not strictly comply with them, do not use this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapour concentrations within safe limits and to protect against toxic or oxygen deficient hazards. Take precautions to avoid skin and eye contact (ie. gloves, goggles, face masks, barrier creams etc.) Actual safety measures are dependant on application methods and work environment.

EMERGENCY CONTACT NUMBERS:

USA/Canada - Medical Advisory Number 1-800-854-6813

Europe - Contact (44) 191 4696111. For advice to Doctors & Hospitals only contact (44) 207 6359191

China – Contact (86) 532 83889090

R.O.W. - Contact Regional Office

Epoxy Tank Coating

LIMITATIONS

This product will not cure adequately below 5°C. For maximum performance ambient curing temperatures should be above 10°C.

International Paint should be consulted to confirm that Interline 704 is suitable for the cargoes to be carried. For maximum performance the curing temperature should be above 10°C.

The drying times and overcoating intervals may alter due to various on-site factors such as tank configuration, ventilation rates, etc. Consult the detailed application procedure for the time interval required between coating completion and cargo loading.

Overcoating information is given for guidance only and is subject to regional variation depending upon local climate and environmental conditions. Consult your local International Paint representative for specific recommendations. Apply in good weather. Temperature of the surface to be coated must be at least 3°C above the dew point. For optimum application properties bring the material to 21-27°C, unless specifically instructed otherwise, prior to mixing and application. Unmixed material (in closed containers) should be maintained in protected storage in accordance with information given in the STORAGE Section of this data sheet. Technical and application data herein is for the purpose of establishing a general guideline of the coating application procedures. Test performance results were obtained in a controlled laboratory environment and International Paint makes no claim that the exhibited published test results, or any other tests, accurately represent results found in all field environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection, verification of performance and use of the coating.

UNIT SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	20 lt	15.56 lt	20 lt	4.44 lt	5 lt

For availability of other unit sizes consult International Paint

UNIT SHIPPING WEIGHT (TYPICAL)	Unit Size	Unit Weight
	20 lt	30.71 Kg

STORAGE	Shelf Life	
		12 months minimum at temperatures up to 25°C. 6 months minimum at temperatures greater than 25°C. Subject to reinspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.

WORLDWIDE AVAILABILITY Consult International Paint.

IMPORTANT NOTE

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

© AkzoNobel, 2015

www.international-marine.com