

Chemflake Special

Product description

This is a glass flake reinforced unsaturated vinyl ester coating. It is an ultra high build, extremely chemical resistant and fast curing barrier coating. Can be used as primer, mid coat or finish coat in atmospheric and immersed environments. Suitable for properly prepared carbon steel and concrete substrates.

Typical use

Specially designed as an internal lining for offshore, onshore and buried tanks and pipes such as chemical tanks, flue gas ducts, cooling towers, funnels, pipes, waste water, grey water, concrete bund, pressure vessels. Specially suitable in acidic conditions. Refer to Protective Product Resistance List. Recommended for areas subject to extreme chemical exposure and mechanical wear and where future maintenance is challenging.

Colours

red, white

Product data

Property	Test/Standard	Description
Solids by volume	calculated	96 ± 2 %
Gloss level (GU 60 °)	ISO 2813	semi gloss (35-70)
Flash point	ISO 3679 Method 1	34 °C
VOC-EU	IED (2010/75/EU) (calculated)	10 g/l

The provided data is typical for factory produced products, subject to slight variation depending on colour.
Gloss description: According to Jotun Performance Coatings' definition.

Film thickness per coat

Typical recommended specification range

Dry film thickness	600 - 1000 µm
Wet film thickness	650 - 1080 µm
Theoretical spreading rate	1,6 - 0,9 m ² /l

All vinyl ester and polyester resin systems are subject to some shrinkage during the curing process. This results in a practical spreading rate lower than the theoretically calculated. The shrinkage depends on actual dry film thickness applied and conditions during application.

Surface preparation

To secure lasting adhesion to the subsequent product all surfaces shall be clean, dry and free from any contamination.

Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Carbon steel	Sa 2½ (ISO 8501-1) with a surface profile Medium to Coarse G (ISO 8503-2)	Sa 2½ (ISO 8501-1) with a surface profile Medium to Coarse G (ISO 8503-2)
Concrete	Dry abrasive blast cleaning to SSPC-SP 13/NACE No. 6.	Minimum 4 weeks curing. Moisture content maximum 5 %. Dry abrasive blast cleaning to SSPC-SP 13/NACE No. 6.

Application

Application methods

The product can be applied by

- Spray: Standard airless spray may be used. Dedicated two component airless spray is an option.
- Brush: Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.

Mixing ratio table - Additives

The steel temperature shall not be lower than the paint temperature and not more than 20 °C above the paint temperature.

Additive volumes (ml) in 16 litres product.

Additive	Paint temperature						
	5-9 °C	10-14 °C	15-19 °C	20-24 °C	25-29 °C	30-34 °C	35-40 °C
Jotun Accelerator CO1P			400	300	300	200	200
Jotun Accelerator DMA10			100	100	100	100	100
Jotun Peroxide 1, Andonox KP-9, Jotun Peroxide 11 or Norox MEKP-925H			400	400	300	300	300
Jotun Inhibitor 53							30

For other additive suppliers please consult Jotun.

WARNING:

Jotun Accelerator and Jotun Peroxide must never come in direct contact with each other.

All peroxides must be stored in a dark and cool storage room (below 25 °C), and kept away from all kind of combustible materials. Exposure to direct sunlight must be avoided. Use only original or approved containers. Empty containers should be washed with water and kept in separate storage/containers. The peroxide may catch fire if exposed to sparks or to hot metal dust from grinding or other mechanical work. The curing reaction develops heat. For leftovers of mixed paint it is recommended to fill the tin with water to avoid excessive heat development.

Thinner/Cleaning solvent

Thinner:	Styrene
Thinning max.:	5 %
Cleaning solvent:	Jotun Thinner No. 17/Jotun Thinner No. 23/Jotun Thinner No. 27

Guiding data for airless spray

Nozzle tip (inch/1000):	27-35
Pressure at nozzle (minimum):	150 bar/2100 psi

Drying and Curing time

Substrate temperature	15 °C	23 °C	40 °C
Surface (touch) dry	8 h	4 h	2 h
Walk-on-dry	8 h	4 h	2 h
Dry to over coat, minimum	8 h	4 h	2 h
Dry to over coat, maximum, immersed	36 h	24 h	12 h
Dried/cured for service	8 d	4 d	2 d

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The shortest time allowed before the next coat can be applied.

Dry to over coat, maximum, immersed: The longest time allowed before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

Induction time and Pot life

Paint temperature	23 °C
Pot life	35 min

Caution

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Colour variation

When applicable, products primarily meant for use as primers or antifoulings may have slight colour variations from batch to batch. Such products may fade and chalk when exposed to sunlight and weathering.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.
