

# Jotafloor Solvent Free Primer

## Product description

This is a two component amine cured solvent free epoxy coating. It is transparent. It ensures very good adhesion on most concrete floors in atmospheric environments only. Specially designed for high build floor coatings on properly prepared concrete substrates.

## Scope

The Application Guide offers product details and recommended practices for the use of this product.

The Application Guide (AG) must be read in conjunction with the relevant specification, Technical Data Sheet (TDS) and Safety Data Sheet (SDS) for all the products used as part of the coating system.

## Referred standards

Reference is generally made to ISO Standards. When using standards from other regions it is recommended to reference only one corresponding standard for the substrate being treated.

## Application

The following restrictions must be observed:

- Only apply the coating when the substrate temperature is at least 3°C above the dew point
- Do not apply the coating if the substrate is wet or likely to become wet
- Do not apply the coating if the weather is clearly deteriorating or unfavourable for application or curing
- Do not apply the coating in high wind conditions

## Product mixing

### Product mixing ratio (by volume)

Jotafloor Solvent Free Primer Comp A	2	part(s)
Jotafloor Solvent Free Primer Comp B (20)	1	part(s)
Jotafloor Solvent Free Primer Comp A	2	part(s)
Jotafloor Solvent Free Primer Comp B (40)	1	part(s)

### Induction time and Pot life

**Paint temperature** **23 °C**

#### Jotafloor Solvent Free Primer Comp B (20)

Pot life 10 min

#### Jotafloor Solvent Free Primer Comp B (40)

Pot life 20 min

# Application Guide

## Jotafloor Solvent Free Primer



Jotafloor Solvent Free Primer Comp B (20) - 30 min. after poured on to the floor.  
Jotafloor Solvent Free Primer Comp B (40) - 45 min. after poured on to the floor.

The temperature of base and curing agent is recommended to be 18 °C or higher when the paint is mixed.

### Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 17

### Application data

#### Other application tools

##### Brush application

Can be used

##### Roller application

Can be done but difficult to achieve a uniform coat. Will most probably give a lot of bubbles. Apply more than one coat but even then difficult to seal off all the pores.

##### Application with trowel

Can be done but difficult to achieve a uniform coat. Will most probably give a lot of bubbles. Apply more than one coat but even then difficult to seal off all the pores.

##### Application with other tools

Use a rubber squeegee after simply pouring out the JF Sealer direct from the drum where mixed with comp.B. Gives a more uniform layer and a much faster application

## Recommended film thickness per coat

Film thickness and spreading rate	Dry film thickness	Wet film thickness	Theoretical spreading rate
	(µm)		(m <sup>2</sup> /l)
Minimum	50	50	20
Maximum	200	200	5
Typical	100	100	10

## Drying and Curing time

Substrate temperature	15 °C	23 °C	40 °C
<b>Jotafloor Solvent Free Primer Comp B (20)</b>			
Surface (touch) dry	7 h	5 h	3 h
Walk-on-dry	25 h	16 h	9 h
Dried to over coat, minimum	24 h	15 h	6 h
Dried to over coat, maximum, atmospheric	72 h	48 h	30 h
Dried/cured for service	10 d	7 d	4 d

#### Jotafloor Solvent Free Primer Comp B (40)

Surface (touch) dry	12 h	10 h	6 h
Walk-on-dry	42 h	30 h	18 h
Dried to over coat, minimum	32 h	24 h	10 h
Dried to over coat, maximum, atmospheric	96 h	72 h	36 h
Dried/cured for service	12 d	9 d	3 d

Drying and curing times are determined under controlled temperatures and relative humidity below 85%, and within the DFT range of the product.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness. Dry sand sprinkled on the surface can be brushed off without sticking to or causing damage to the surface.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dried to over coat, minimum: The shortest time allowed before the next coat can be applied.

Dried to over coat, maximum, atmospheric: The longest time allowed before the next coat can be applied without any surface preparation.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

## Maximum over coating intervals for atmospheric exposure

Substrate temperature	15 °C	23 °C	40 °C
<b>Jotafloor Solvent Free Primer Comp B (20)</b>			
Itself	3 d	2 d	1 d
epoxy	3 d	2 d	1 d
polyurethane	3 d	2 d	1 d
<b>Jotafloor Solvent Free Primer Comp B (40)</b>			
Itself	4 d	3 d	1.5 d
epoxy	4 d	3 d	1.5 d
polyurethane	4 d	3 d	1.5 d

## Other conditions that can affect drying / curing / over coating

### Repair of coating system

Damages to the coating layers:

Prepare the area through sandpapering or grinding, followed by thorough washing. When the surface is dry the coating may be over coated by itself or by another product, ref. original specification.

Always observe the maximum over coating intervals. If the maximum over coating interval is exceeded the surface should be carefully roughened in order to ensure good intercoat adhesion. Damages exposing bare substrate:

Remove all rust, loose paint, grease or other contaminants by spot abrasive blasting, mechanical grinding, water and/or solvent washing. Feather edges and roughen the overlap zone of surrounding intact coating. Apply the coating system specified for repair.

## Quality assurance

The following information is the minimum recommended. The specification may have additional requirements.

- Confirm all welding and other metal work, whether internal or external to the tank, has been completed before commencing pre-treatment and surface preparation of the substrate
- Confirm installed ventilation is balanced and has the capacity to deliver and maintain the RAQ
- Confirm the required surface preparation standard has been achieved and is held prior to coating application
- Confirm that the climatic conditions are within recommendation in the AG and held during the application
- Confirm the required number of stripe coats have been applied
- Confirm each coat meets the DFT requirements of the specification
- Confirm the coating has not been adversely affected by rain or any other agency during curing
- Observe adequate coverage has been achieved on corners, crevices, edges and surfaces where the spray gun cannot be positioned so that its spray impinges on the surface at 90°
- Observe the coating is free from defects, discontinuities, insects, spent abrasive media and other contamination
- Observe the coating is free from misses, sags, runs, wrinkles, fat edges, mud cracking, blistering, obvious pinholes, excessive dry spray, heavy brush marks and excessive film build
- Observe the uniformity and colour are satisfactory

All noted defects should be fully repaired to conform to the coating specification.

## Caution

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

For further advice please contact your local Jotun office.

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

## Accuracy of information

Always refer to and use the current (last issued) version of the TDS, SDS and if available, the AG for this product. Always refer to and use the current (last issued) version of all International and Local Authority Standards referred to in the TDS, AG & SDS for this product.

## Colour variation

Some coatings used as the final coat may fade and chalk in time when exposed to sunlight and weathering effects. Coatings designed for high temperature service can undergo colour changes without affecting performance. Some slight colour variation can occur from batch to batch. When long term colour and gloss retention is required, please seek advice from your local Jotun office for assistance in selection of the most suitable top coat for the exposure conditions and durability requirements.

## Reference to related documents

The Application Guide (AG) must be read in conjunction with the relevant specification, Technical Data Sheet (TDS) and Safety Data Sheet (SDS) for all the products used as part of the coating system.

When applicable, refer to the separate application procedure for Jotun products that are approved to classification societies such as PSPC, IMO etc.

## Symbols and abbreviations

min = minutes  
h = hours  
d = days

TDS = Technical Data Sheet  
AG = Application Guide  
SDS = Safety Data Sheet

°C = degree Celsius  
° = unit of angle  
µm = microns = micrometres  
g/l = grams per litre  
g/kg = grams per kilogram  
m<sup>2</sup>/l = square metres per litre  
mg/m<sup>2</sup> = milligrams per square metre  
psi = unit of pressure, pounds/inch<sup>2</sup>  
Bar = unit of pressure  
RH = Relative humidity (% RH)  
UV = Ultraviolet  
DFT = dry film thickness  
WFT = wet film thickness

VOC = Volatile Organic Compound  
MCI = Jotun Multi Colour Industry (tinted colour)  
RAQ = Required air quantity  
PPE = Personal Protective Equipment  
EU = European Union  
UK = United Kingdom  
EPA = Environmental Protection Agency  
ISO = International Standards Organisation  
ASTM = American Society of Testing and Materials  
AS/NZS = Australian/New Zealand Standards  
NACE = National Association of Corrosion Engineers  
SSPC = The Society for Protective Coatings  
PSPC = Performance Standard for Protective Coatings  
IMO = International Maritime Organization

---

## Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.

---